





TRADITIONAL



San Diego Buff



Taupe




Burnt Sienna



Nutmeg



Terra Cotta



Bedrock




Brick



Brown Suede




Sunset Blush




Concrete Gray



Marigold




Pewter




Sierra



Hunter Green



Black



Slate



Granite



SOLAR-REFLECTIVE




SR Sandstone
Reflectance: .32
Emittance: .94

(SRI = 36)




SR Khaki
Reflectance: .33
Emittance: .94

(SRI = 37)



SR Irish Cream
Reflectance: .43
Emittance: .94

(SRI = 50)




SR White
Reflectance: .60
Emittance: .94

(SRI = 73)



SR Fawn
Reflectance: .31
Emittance: .93

(SRI = 35)



SR Sun Baked Clay
Reflectance: .44
Emittance: .95

(SRI = 52)




SR Brownstone
Reflectance: .30
Emittance: .90

(SRI = 31)




SR Terra Cotta
Reflectance: .31
Emittance: .92

(SRI = 33)




SR Evergreen
Reflectance: .32
Emittance: .88

(SRI = 33)



SR Safety Blue
Reflectance: .30
Emittance: .93

(SRI = 33)



SR Slate
Reflectance: .31
Emittance: .91


(SRI = 34)

DecoCoat Colorants can contribute to LEED points.

Note: Reflectance values are measured in accordance with American Standard of Testing Methodology (ASTM) C1549. Emittance values are measured in accordance with ASTM C1371. The SRI values of DecoCoat are calculated according to ASTM E1980-01.




CYCLE LANES



CL Shamrock Green



CL Celtic Green




CL Emerald Green




SIGNATURE




Sandy Beige



Driftwood



Butterscotch



Pumpkin Spice



Chestnut Brown




Mocha




Mustard



Down To Earth




Paprika




Avocado



Sea Foam



Aqua




Sage




Truffle




Patriot Blue



Cobalt Blue




Gun Metal



Merlot



Smokey Mauve



Graphite



Bike Path Green